



Mapegrout SV T

Quick-setting and hardening, shrinkage compensated, thixotropic mortar for repairing concrete and fixing drains, manholes and urban fixtures



WHERE TO USE

- Repairing concrete elements, including those on a slope.
- Repairing industrial floors, and for construction work on roads and in airports which need to be quickly reopened to traffic.
- Fixing inspection shafts and manholes in place.

Some application examples

- Repairing concrete floors used in industry, shopping centres and warehouses.
- Repairing concrete road surfaces in airports.
- Repairing roadside pavements.
- Repairing access ramps.
- Repairing concrete overflow channels.
- Fixing road signs in place.
- Fixing concrete electricity and telephone pylons in place.
- Fixing fences in place.
- Fixing urban fixtures in place.
- Anchoring protective barriers and crash barriers in place.

- Fixing gratings for overflow channels in central reservations and kerbstones in place.
- Fixing drain covers and manhole covers for gas, electricity and phone companies in place.

TECHNICAL CHARACTERISTICS

Mapegrout SV T is a one-component, pre-blended, shrinkage compensated thixotropic black mortar in powder form, made from special hydraulic binders, high-strength cement, graded aggregates and special admixtures according to a formula developed in MAPEI's own research laboratories.

Mapegrout SV T is suitable also where large thicknesses need to be applied (up to 5 cm), in specially-prepared areas without the use of formwork.

Thanks to its rapid hardening properties, **Mapegrout SV T** may be stepped on and opened to rubber-wheeled traffic after only 2 hours from application at a temperature of +20°C. Thanks to its special composition and the admixtures contained in the product, the mortar has high mechanical properties even after a long period of time, is impermeable to water and is considerably resistant to abrasion.

Mapegrout SV T meets the requirements defined by EN 1504-9 (*"Products and systems for the protection and repair of concrete structures - Definitions, requirements, quality control and evaluation of conformity - General principles for the use of products and systems"*) and the minimum requirements claimed

by EN 1504-3 (“*Structural and non structural repair*”) for structural mortars of class R4.

RECOMMENDATIONS

- Do not add cement or admixtures to **Mapegrout SV T**.
- Do not use **Mapegrout SV T** if the bag is damaged.
- Do not add water once the mix has started to set.
- Do not apply **Mapegrout SV T** on asphalted surfaces or on surfaces treated with bitumen.
- If the surface is subject to heavy traffic and dynamic stress and vibration, we recommend adding metallic fibres to the product.
- Do not apply **Mapegrout SV T** on smooth surfaces. Substrates must have a rough surface (at least 5 mm of roughness) and, if necessary, reinforcement rods may be inserted.
- Do not use **Mapegrout SV T** if the temperature is lower than +5°C or higher than +35°C. If the product is to be applied at temperatures not included within this range, please consult our Technical Services Department.
- **Mapegrout SV T** sets very quickly. Therefore, we recommend mixing only quantities of the product which will be laid within 10 minutes of preparation.

APPLICATION PROCEDURE

Preparation of the substrate

- Remove all concrete which has deteriorated or is at risk of detachment, until a solid, strong rough substrate is obtained. Remove all loose parts with a hydro jack-hammer. All previous repair work which is not perfectly bonded must be removed.
- Eliminate all old paintwork, oil, dust and any other material which may impede the bonding of **Mapegrout SV T** to the substrate.
- Saturate the substrate with water.
- Before applying the product, wait until all excess water has evaporated. If necessary, use compressed air.

Preparing the mortar

- Pour 12.5-13.5% of water into a cement mixer (3.1-3.4 litres per 25 kg bag). Slowly add **Mapegrout SV T** and mix for 1-2 minutes. Remove all the powder which has not blended with the mix from the sides of the mixer and continue mixing for 2-3 minutes, until a smooth, homogenous blend is obtained.

Laying the mortar

- Apply **Mapegrout SV T** using a trowel in the pre-prepared area.

- Compact the mortar to get rid of any voids, either manually with a trowel or with a vibrator with a pronged fitting.
- Smooth off the surface immediately with a finishing trowel.

If required, after fixing drain covers or man-hole covers in place, lay fresh asphalt around the area. We recommend applying a layer of at least 3 cm thick in order to bond well and to bear the weight of traffic without cracking.

PRECAUTIONS TO BE TAKEN DURING AND AFTER APPLICATION In cold weather

- Make sure the substrate is not frozen, and protect the product from frost for 24 hours after laying.
- Mix the product with tepid water.
- Before use, store the product in an area protected against damp and frost.

In hot and/or windy weather

- Saturate the substrate with water.
- Mix the product with cold water.
- Protect the fresh mortar surface against rapid evaporation of the water with **Mapecure S** or **Mapecure E** to avoid the formation of shrinkage cracks.

Cleaning

While still fresh, the mortar may be removed from work tools with running water. Once set, it is difficult to remove the mortar and cleaning must be carried out using mechanical means.

COLOURS

Black.

CONSUMPTION

20 kg/m² per cm of thickness.

PACKAGING

25 kg bags.

STORAGE

The product remains stable for 12 months if stored in its original packaging.

The product complies with the conditions of Annex XVII to Regulation (EC) N° 1907/2006 (REACH), item 47.

The product is available in special 25 kg vacuum-packed polyethylene bags which may be stored outside for the entire construction phase of the site. Rain has no effect on its characteristics.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Mapegrout SV T is irritant, it contains cement that when in contact with sweat or other body fluids causes irritant alkaline reaction and allergic reactions to those predisposed. In case of contact with eyes or skin wash immediately with plenty of water and seek medical attention. It is recommended to use protective gloves and goggles.

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

Class according to EN 1504-3:	R4
Type:	CC
Consistency:	powder
Colour:	black
Maximum size of aggregate (mm):	2.5
Bulk density (kg/m³):	1,300
Dry solids content (%):	100
Chloride ions content: - minimum requirements $\leq 0,05\%$ - according to EN 1015-17 (%):	≤ 0.05

APPLICATION DATA (at +20°C - 50% R.H.)

Colour of mix:	black
Mixing ratio:	100 parts of Mapegrout SV T with 12.5-13.5 parts of water (3.1-3.4 l of water for every 25 kg bag)
Consistency of mix:	plastic-thixotropic
Density of mix (kg/m³):	2,250
pH of mix:	> 12
Application temperature range:	from +5°C to +35°C
Application temperature:	+5°C +10°C +20°C
Pot life of mix:	30' 15' 10'
Final hardening:	100' 60' 35'

FINAL PERFORMANCE (blending water 13%)

Performance characteristic	Test method	Minimum requirements according to EN 1504-3 for R4 class mortar	Product performance			
			+5°C	+10°C	+20°C	
Compressive strength (MPa):	EN 12190	≥ 45 (after 28 days)	2 h	2	10	17
			4 h	10	15	20
			1 day	20	22	25
			7 days	25	27	30
			28 days	45	45	45
Flexural strength (MPa):	EN 196/1	not required	+5°C	+10°C	+20°C	
			2 h	1.0	2.0	2.0
			4 h	2.5	3.0	3.5
			1 day	4.5	4.5	5.0
			7 days	5.5	5.5	5.5
28 days	6.0	6.0	6.0			
Modulus of elasticity in compression (GPa):	EN 13412	≥ 20 (after 28 days)	25 (after 28 days)			
Bond strength to concrete (MC 0.40 type substrate - water/cement ratio = 0.40) according to EN 1766 (MPa):	EN 1542	≥ 2 (after 28 days)	> 2 (after 28 days)			
Resistance to accelerated carbonation:	EN 13295	Depth of carbonation \leq reference concrete (MC 0.45 type with water/cement ratio = 0.45) according to UNI 1766	test passed			
Capillary absorption (kg/m²·h^{0.5}):	EN 13057	≤ 0.5	< 0.5			
Thermal compatibility to freeze-thaw cycles with deicing salts, measured as according to EN 1542 (MPa):	EN 13687/1	≥ 2 (after 50 cycles)	> 2			
Reaction to fire:	EN 13501-1	Euroclass	A1			

Mapegrout SVT



For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the

product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

All relevant references for the product are available upon request and from www.mapei.com



BUILDING THE FUTURE