

Heratekta C-3 **Heratekta C-3 F**

Wood wool insulation
and soundproof board

Heraklith®



Heratekta C-3, C-3 F

Three-layer composite board with a core of EPS slab and wood wool facing with cement binder.

Product norm: EN 13168

EC Certificate of Conformity Reg. Number: K1 -0751 -CPD-209.0-01-05/12

Designation code: WW-EN 13168 - L1-W1-T1-S1-P1-CS(10)50-TR5-C11

PRODUCT DESCRIPTION

Composite board made from EPS hard foam core and two-sided wood wool facing with cement binder according to EN 13168..

APPLICATION AREA

Thermal insulation of facades, slabs, and garages, permanent formwork for eliminating thermal bridges, insulation of slabs cooled from beneath. It provides an impact resistant surface and a perfect base for renders thanks to the solid wood wool layer with cement binder.

TECHNICAL PROPERTIES

- Excellent thermal insulation
- It can be used as a permanent formwork
- Very good acoustic characteristics
- Low vapour resistance
- Excellent construction-biological properties
- Resistant to microorganisms and rodents
- Chemically neutral – no reaction with the surrounding materials
- No mass and dimensional changes in case of temperature differences
- Easy cutting to the requested size and shape
- Very high resistance to mechanical stresses

PRODUCTION SIZES, PACKAGING UNITS

Thickness	mm	25	35	50	75	100	125	150
Layers	mm	5/15/5	5/25/5	5/40/5	5/65/5	5/90/5	5/115/5	5/140/5
Average mass	kg/m ²	8,5	8,5	9,0	9,0	9,5	10,0	10,5
Packaging unit	pc/pallet	42	32	22	14	11	8	7
Length	mm	2 000*						
Width	mm	600**						

Transportation: on pallets. Packaging: wrapped in foil, strapped on two positions.

* Boards can be ordered in half length (1000 mm), as well. ** 500 mm width is available on request.

TECHNICAL DETAILS

Properties	Sign	Description/Data							Unit	Norm
Fire class	-	E							-	EN 13501-1
Thermal conductivity - WW/EPS	λ_D	EPS (Core): 0,040 Woodwool (Facing): 0,070							[W/mK]	EN 13168
Thickness	d	25	35	50	75	100	125	150	[mm]	
Thermal resistance - declared value	R_D	0,50	0,75	1,10	1,75	2,35	3,00	3,60	[m ² K/W]	EN 13168
Compression strength	σ_m	≥ 50							[kPa]	EN 826
Tensile strength perpendicular to faces	σ_{MT}	≥ 5							[kPa]	EN 1607
Vapour diffusion resistance factor	μ	20							-	EN 12086

Dimensional stability and tolerances of WW boards

Due to the organic component of wood wool boards slight deviations in the size cannot be excluded. Likewise, the panels also shrink and expand if there is strongly fluctuating air humidity.

- Dimensional stability in standard climatic conditions is 0,5% for length (± 10 mm for 2000 mm boards) and for width (± 2,5 mm for 600 mm wide boards).

Therefore, special attention must be given to the temperature and air humidity during installation (if necessary heat, ventilate, or dehumidify the air under constant monitoring) in order to ensure the required installation conditions.

- Production tolerance for the 2000 mm nominal dimensions is +5/-10 mm; for 1000 mm lengths +3/-5 mm, for width is ± 3 mm according to EN 13168 point 4.2.2.

Installation and system conditions

- The installation of WW products (Herakliith homogeneous boards, Heratekta and Tektalan composite boards) must be carried out under controlled humidity and temperature conditions.
- Only install panels in rooms, where the following conditions are ensured: for heated or air-conditioned rooms, the maximum relative air humidity must be between 40% and 75%, the temperature must not be below +7°C or above +30°C.
- If WW products are to be installed in rooms with central heating, or in rooms with conditions significantly different from normal conditions we recommend acclimatising the boards for at least 48 hours days in a room with the same climatic conditions.

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work activities presented in this document is not permitted. Extreme care was observed when putting together the information, texts and illustrations in this document. Nevertheless, errors cannot be completely ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof. The publisher and editors will be grateful for suggestions for improvement and notification of any errors.

Knauf Insulation Kft.

H-8924 Alsónemesapáti, Ipartelep

H-8901 Zalaegerszeg Pf. 303.

Tel.: +36 92 550 900

Fax: +36 92 550 901

info.hu@knaufinsulation.com

www.knaufinsulation.hu

Herakliith® is a registered trademark of

KNAUFINSULATION
it's time to save energy